# HANGZHOU HANHAO CHEMICAL CO., LTD

**Plant:** Jiangdong Development Zone, Great Jiangdong District, Hangzhou China **Office:** 2103 Bldg1, Dacheng Plaza, Shixin Road, Xiaoshan, Hangzhou, China **Tel:**+86-571-82502631/82551631 **Fax:**+86-571-82722631

#### TECHNICAL DATA SHEET

#### **Product Description:**

Product Name: Molybdate Red G207
Color Index: Pigment Red 104

C.I.No. 77605 CAS No. 12656-85-8

Chemical Nature: Inorganic Pigment

Chemical Formula xPbCrO<sub>4</sub>·yPbSO<sub>4</sub>·ZPbMoO<sub>4</sub>

# **Technical Properties:**

It is Bright color, strong tinting strength, high hiding with good light fastness and excellent water, wax, solvent resistance and good acid, alkali fastness.

# **Application:**

Recommend: Inks, Coatings, Plastic and Rubber

### **Color Shade and tinting strength**

| Item                     |  |  |        |                              | Standard                      |
|--------------------------|--|--|--------|------------------------------|-------------------------------|
|                          | Minimum                                |  | Maximu | n                            | Test way                      |
| <b>Binding Materials</b> | The refined linseed oil (4)            |  |        |                              |                               |
| Color Shade              | Similar                                |  |        | DIN ISO787 Part 1; GB/T 1864 |                               |
| Tinting Shade            | Similar                                |  |        |                              | GB/T 5211.19                  |
| Binder                   | Offset printing ink resin(10-40 white) |  |        |                              |                               |
| <b>Tinting Strength</b>  | 95                                     |  |        | AY                           | No.038,2009-08-01;GB/T5211.19 |

#### **Technical Data**

| Item                 | Minimum | Maximum | Test way                       |
|----------------------|---------|---------|--------------------------------|
| Water Soluble Matter |         | 1.0     | DIN ISO787 Part 3;GB/T 5211.1  |
| PH value             | 4       | 7.0     | DIN ISO787 Part 9;GB/T 1717    |
| Volatile Matter 105℃ |         | 2.5     | DIN ISO787 Part 2;GB/T 5211.3  |
| Residue on           |         | 0.5     | DIN 53195 GB/T 1715            |
| sieve(0.045mm) %     |         |         |                                |
| Hiding Power g/m     |         | 60.0    | GB/T1709                       |
| Oil Absorption (g /  |         | 23.0    | DIN ISO787 Part 5;GB/T 5211.15 |
| 100g)                |         |         |                                |

Note: The above information is provided as guidelines for your reference only. The accurate effects should base on the test results in laboratory.

# **Transport and storage**

During transport should prevent rain, sunlight exposure, loading and unloading must be light, light relief, prevents breakage, obey the traffic rules. Product should be stored in ventilated, dry and cool warehouse, must be isolated from the acid, alkali and other chemicals and flame. Package products have been opened: sealed packaging in order to prevent absorption of moisture and contamination..

